

LNP™ STAT-KON™ COMPOUND EEF42

ECF-1006
REGION ASIA

DESCRIPTION

LNP STAT-KON* EEF42 is a compound based on Polyetherimide resin containing 10% Carbon Fiber, 20% Glass Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	194	MPa	ASTM D 638
Tensile Strain, break	1.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	15850	MPa	ASTM D 638
Flexural Stress	275	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	507	J/m	ASTM D 4812
Izod Impact, notched, 23°C	71	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	211	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.34E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	2.33E-05	1/°C	ASTM E 831
PHYSICAL			
Density	1.46	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.1 – 0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 – 0.4	%	ASTM D 955
ELECTRICAL			
Volume Resistivity	10000000000 – 100000000000	Ohm-cm	ASTM D 257
MECHANICAL PROPERTIES			
Flexural modulus	15850	MPa	ISO 178/1A
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	360 – 365	°C	
Front - Zone 3 Temperature	365 – 375	°C	
Middle - Zone 2 Temperature	355 – 365	°C	
Rear - Zone 1 Temperature	345 – 355	°C	
Mold Temperature	120 – 150	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.