

LEXAN™ COPOLYMER HFD4472

REGION AMERICAS

DESCRIPTION

LEXAN HFD4472 is a 20% glass filled, medium flow, impact modified, injection moldable grade designed for high flow and superior surface appearance. HFD4472 has enhanced mold release, impact ductility and broad color space.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	54	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	56	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	5500	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4900	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	54	MPa	ISO 527
Tensile Stress, break, 5 mm/min	56	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
IMPACT			
Izod Impact, unnotched, 23°C	800	J/m	ASTM D 4812
Izod Impact, notched, 23°C	190	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	30	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	47	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	43	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	18	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	13	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	21	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	13	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	59	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	59	kJ/m ²	ISO 179/1eU
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	132	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	128	°C	ASTM D 648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	3.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	3.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.33	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.2 – 0.3	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm (5)	0.4 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D 1238
Density	1.33	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	9	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Constant, 1.9 GHz	3.16	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0099	-	SABIC method
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	0.4	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	290 – 310	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	290 – 310	°C	
Middle - Zone 2 Temperature	275 – 300	°C	
Rear - Zone 1 Temperature	265 – 290	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.