

LNP™ STAT-KON™ COMPOUND MX01767C

PDX-M-01767 CCS
REGION AMERICAS

DESCRIPTION

LNP STAT-KON MX01767C is a compound based on Polypropylene containing Proprietary Filler(s). Added features of this grade include: Electrically Conductive, Clean Compounding System.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	32	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	20	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	7.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	25.5	%	ASTM D 638
Tensile Modulus, 5 mm/min	1760	MPa	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	1490	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	31	MPa	ISO 527
Tensile Stress, break, 5 mm/min	22	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6.6	%	ISO 527
Tensile Strain, break, 5 mm/min	18	%	ISO 527
Tensile Modulus, 1 mm/min	1570	MPa	ISO 527
Flexural Stress	35	MPa	ISO 178
Flexural Modulus, 2 mm/min	1510	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1470	J/m	ASTM D 4812
Izod Impact, notched, 23°C	130	J/m	ASTM D 256
Multiaxial Impact	32	J	ISO 6603
Instrumented Impact Total Energy, 23°C	37	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	141	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	95	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	53	°C	ASTM D 648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	9.2E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.5E-05	1/°C	ASTM E 831
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	89	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	52	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	0.98	-	ASTM D 792
Density	0.98	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.02	%	ASTM D 570
Mold Shrinkage, flow (5)	1	%	SABIC method
Mold Shrinkage, xflow (5)	2	%	SABIC method
Moisture Absorption (23°C / 50% RH)	0.01	%	ISO 62
ELECTRICAL			
Surface Resistivity	3.E+00	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Melt Temperature	225 – 250	°C	
Front - Zone 3 Temperature	240 – 250	°C	
Middle - Zone 2 Temperature	215 – 225	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	30 – 50	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.